



BLACK-TECH

**SPECIALIZED PAINT - BLACK MATT
FOR WALLS, PVC, GLASS, WOOD, TILES**

DESTINY:

Water-soluble paint intended for painting walls and ceilings indoors.

It is characterized by deep black, recommended for use in theaters, cinemas, stages and ceilings. above suspended ceilings and in installation channels, false ceiling spaces together with installations ventilation in insulation, residential buildings (bathrooms, kitchens) and public buildings.

Creates a smooth, very well-covering, vapor-permeable coating on a variety of materials.

construction, such as: mineral plasters (gypsum, cement, cement-lime, silicate and polymer

(e.g. acrylic), bricks, concrete, wood-based materials, plasterboard, sheet metal, aluminum,

glass fiber and paper wallpapers. It can be used on steel surfaces after prior

covering the substrate with AKRYLEN GRUNT or EPIMAL STAL. The dirty surface can be washed with water

with the addition of mild detergents using a cloth or soft brush.

SURFACE PREPARATION AND APPLICATION:

The paint is ready to use. Before use, mix the contents of the package thoroughly. In case

thickening, you can add up to 5% water. Do not add chalk, lime or other similar materials.

The surface to be painted should be thoroughly cleaned, loose paint flakes removed, degreased,

dry. Old layers of glue and lime paints must be removed without fail. Fresh cement-lime plasters can be painted no earlier than

3-4 weeks after application. Smooth surfaces should be matted

sandpaper and vacuum. Fill any gaps and cracks with BIEL-PUTZ or FILLER acrylic putty.

Pigment, larger defects - with gypsum. Raw, dusty, inconsistent or excessively water-absorbing substrates should be

prime with BIEL-GRUNT, GRUNDER PC-33 or Pigment Primer.

AFTER USING PIGMENT MULTICONTACT, IT CAN BE USED ON METAL, PVC, GLASS,

WOOD, TILES.

DEVICE	PRESSURE, BAR	NOZZLE	FILTER, MESH	RECOMMENDED DILUTION
GRACO GX 21	170	LP 512	60	-



BLACK-TECH

COMMENTS:

Due to the variety of technologies and raw materials used in products by other manufacturers, the manufacturer is not responsible for the consequences of mixing its product with other products. The paint should be store in original and tightly closed packaging. The room before being put into air out the odor until it disappears. Keep out of reach of children. In case of eye contamination, rinse with plenty of water. EUH208 - Contains a mixture of 5-chloro-2-methyl-3(2H)-isothiazolone and 2-methyl-3(2H)-isothiazolone. May cause allergic reactions. If eye irritation occurs or if swallowed seek medical advice immediately, show the packaging or label. Product classified as A/a/FW, the permissible VOC content for this category is 30 g/l. The paint contains less than 30 g/l.

available colors:	black
coating:	matte
paint:	with a roller, brush or, after appropriate dilution, by spraying
use and store at temperature:	5÷30°C
drying time, depending on the substrate and environmental conditions:	approx. 2 hours
recommended number of layers:	2
applying the next layer:	after 3-4 hours
performance:	8-10 m²/L
density according to PN-82/C-81551:	ok. 1,50 g/cm³
water vapor transmission coefficient:	medium 15 < V < 150 g/(m²•24 h); 0.14 < sd < 1.4 m
pH value:	8÷9
equipment cleaning and dilution:	water
warranty:	18 months from the production date (located on the cover)
packaging:	5 L; 10 L

When a new version of the card appears, the previous card becomes invalid.
ver.20221220